

**AMENDMENTS TO THE CLAIMS**

1-156. (Canceled)

157 (New). A semiconductor light-emitting device constituted by mounting a semiconductor light-emitting element on a base substance, wherein

the semiconductor light-emitting element has outgoing light having an emission wavelength of 390 to 420 nm; and

there is included a fluorescent substance that is excited by outgoing light from the semiconductor light-emitting element and emits red light having an emission wavelength with its main emission peak in a wavelength range of 600 to 670 nm, wherein

the fluorescent substance is composed of any one or more selected from a fluorescent substance group consisting of:

$M_2 O_2 S : Eu$  (M is any one or more elements selected from La, Gd and Y);

$0.5 MgF_2 \cdot 3.5 MgO \cdot GeO_2 : Mn$ ;

$Y_2 O_3 : Eu$ ;

$Y(P, V) O_4 : Eu$ ; and

$YVO_4 : Eu$ .

158 (New). A semiconductor light-emitting device constituted by mounting a semiconductor light-emitting element on a base substance, wherein

the semiconductor light-emitting element has outgoing light having an emission wavelength in a range of 390 to 420 nm; and

there is included a fluorescent substance that is excited by outgoing light from the semiconductor light-emitting element and emits green light having an emission wavelength with its main emission peak in a wavelength range of 500 to 540 nm, wherein

the fluorescent substance is composed of any one or more selected from a fluorescent substance group consisting of:

$\text{RMg}_2\text{Al}_{16}\text{O}_{27}$  : Eu, Mn (R is any one or both elements selected from Sr and Ba);

$\text{RMgAl}_{10}\text{O}_{17}$  : Eu, Mn (R is any one or both elements selected from Sr and Ba);

$\text{ZnS}$ : Cu;

$\text{SrAl}_2\text{O}_4$  : Eu;

$\text{SrAl}_2\text{O}_4$  : Eu, Dy;

$\text{ZnO}$ : Zn;

$\text{Zn}_2\text{Ge}_2\text{O}_4$  : Mn;

$\text{Zn}_2\text{SiO}_4$  : Mn; and

$\text{Q}_3\text{MgSi}_2\text{O}_8$  : Eu, Mn (Q is any one or more elements selected from Sr, Ba and Ca).

159 (New). A semiconductor light-emitting device constituted by mounting a semiconductor light-emitting element on a base substance, wherein

the semiconductor light-emitting element has outgoing light having an emission wavelength in a range of 390 to 420 nm; and

there is included a fluorescent substance that is excited by outgoing light from the semiconductor light-emitting element and emits blue light having an emission wavelength with its main emission peak in a wavelength range of 410 to 480 nm, wherein

the fluorescent substance is composed of any one or more selected from a fluorescent substance group consisting of:

$A_{10}(PO_4)_6Cl_2 : Eu$  (A is any one or more elements selected from Sr, Ca, Ba, Mg and Ce);

$XMg_2Al_{16}O_{27} : Eu$  (X is any one or both elements selected from Sr and Ba);

$XMgAl_{10}O_{17} : Eu$  (X is any one or both elements selected from Sr and Ba);

$ZnS : Ag$ ;

$Sr_{10}(PO_4)_6Cl_2 : Eu$ ;

$Ca_{10}(PO_4)_6F_2 : Sb$ ;

$Z_3MgSi_2O_8 : Eu$  (Z is any one or more elements selected from Sr, Ca and Ba);

$SrMgSi_2O_8 : Eu$ ;

$Sr_2P_2O_7 : Eu$ ; and

$CaAl_2O_4 : Eu, Nd$ .

160 (New). A semiconductor light-emitting device constituted by mounting a semiconductor light-emitting element on a base substance, wherein

the semiconductor light-emitting element has outgoing light having an emission wavelength in a range of 390 to 420 nm; and

there is included a fluorescent substance that is excited by outgoing light from the semiconductor light-emitting element and emits blue green light having an emission wavelength with its main emission peak in a wavelength range of 480 to 500 nm, wherein

the fluorescent substance is composed of any one or more selected from a fluorescent substance group consisting of:

$\text{Sr}_4 \text{Al}_{14} \text{O}_{25} : \text{Eu}$ ;

$\text{Sr}_4 \text{Al}_{14} \text{O}_{25} : \text{Eu, Dy}$ ;

$\text{L}_{10} (\text{PO}_4)_6 \text{Cl}_2 : \text{Eu}$  (L is any one or more elements selected from Ba, Ca and Mg);

and

$\text{Sr}_2 \text{Si}_3 \text{O}_8 \cdot 2\text{SrCl}_2 : \text{Eu}$ .

161 (New). A semiconductor light-emitting device constituted by mounting a semiconductor light-emitting element on a base substance, wherein

the semiconductor light-emitting element has outgoing light having an emission wavelength in a range of 390 to 420 nm; and

there is included a fluorescent substance that is excited by outgoing light from the semiconductor light-emitting element and emits orange light having an emission wavelength with its main emission peak in a wavelength range of 570 to 600 nm.

162 (New). The semiconductor light-emitting device according to Claim 161, wherein the fluorescent substance is composed of any one or more selected from a fluorescent substance group consisting of:

$\text{ZnS} : \text{Mn}$ ; and

ZnS: Cu, Mn, Co.

- 163 (New). The semiconductor light-emitting device according to Claim 157, wherein
- a sealing resin for sealing at least a part of the base substance and the semiconductor light-emitting element is included; and
- the sealing resin contains the fluorescent substance.
- 164 (New). The semiconductor light-emitting device according to Claim 158, wherein
- a sealing resin for sealing at least a part of the base substance and the semiconductor light-emitting element is included; and
- the sealing resin contains the fluorescent substance.
- 165 (New). The semiconductor light-emitting device according to Claim 159, wherein
- a sealing resin for sealing at least a part of the base substance and the semiconductor light-emitting element is included; and
- the sealing resin contains the fluorescent substance.
- 166 (New). The semiconductor light-emitting device according to Claim 160, wherein
- a sealing resin for sealing at least a part of the base substance and the semiconductor light-emitting element is included; and
- the sealing resin contains the fluorescent substance.
- 167 (New). The semiconductor light-emitting device according to Claim 161, wherein

a sealing resin for sealing at least a part of the base substance and the semiconductor light-emitting element is included; and

the sealing resin contains the fluorescent substance.

168 (New). The semiconductor light-emitting device according to Claim 163, wherein

the base substance is a lead frame having a cup-shaped mount section;

the semiconductor light-emitting element is disposed at the bottom of the cup-shaped mount section of the lead frame and electrically connected to another lead frame by wire bonding; and

at least a part of the two lead frames and the semiconductor light-emitting element are sealed with the sealing resin.

169 (New). The semiconductor light-emitting device according to Claim 163, wherein

the base substance is an insulator connected to ends of a pair of lead frames;

the semiconductor light-emitting element is connected to metallic wiring formed on the insulator; and

at least a part of the pair of lead frames, the insulator and the semiconductor light-emitting element are sealed with the sealing resin.

170 (New). The semiconductor light-emitting device according to Claim 157, wherein

the base substance is a lead frame having a cup-shaped mount section;

the semiconductor light-emitting element is disposed at the bottom of the cup-shaped mount section of the lead frame and electrically connected to another lead frame by wire bonding;

the fluorescent substance is filled in the cup-shaped mount section; and

at least a part of the two lead frames, the semiconductor light-emitting element and the fluorescent substance are sealed with a sealing resin.

171 (New). The semiconductor light-emitting device according to Claim 158, wherein

the base substance is a lead frame having a cup-shaped mount section;

the semiconductor light-emitting element is disposed at the bottom of the cup-shaped mount section of the lead frame and electrically connected to another lead frame by wire bonding;

the fluorescent substance is filled in the cup-shaped mount section; and

at least a part of the two lead frames, the semiconductor light-emitting element and the fluorescent substance are sealed with a sealing resin.

172. (Currently amended) The semiconductor light-emitting device according to Claim 159, wherein

the base substance is a lead frame having a cup-shaped mount section;

the semiconductor light-emitting element is disposed at the bottom of the cup-shaped mount section of the lead frame and electrically connected to another lead frame by wire bonding;

the fluorescent substance is filled in the cup-shaped mount section; and

at least a part of the two lead frames, the semiconductor light-emitting element and the fluorescent substance are sealed with a sealing resin.

173 (New). The semiconductor light-emitting device according to Claim 160, wherein

the base substance is a lead frame having a cup-shaped mount section;

the semiconductor light-emitting element is disposed at the bottom of the cup-shaped mount section of the lead frame and electrically connected to another lead frame by wire bonding;

the fluorescent substance is filled in the cup-shaped mount section; and

at least a part of the two lead frames, the semiconductor light-emitting element and the fluorescent substance are sealed with a sealing resin.

174 (New). The semiconductor light-emitting device according to Claim 161, wherein

the base substance is a lead frame having a cup-shaped mount section;

the semiconductor light-emitting element is disposed at the bottom of the cup-shaped mount section of the lead frame and electrically connected to another lead frame by wire bonding;

the fluorescent substance is filled in the cup-shaped mount section; and

at least a part of the two lead frames, the semiconductor light-emitting element and the fluorescent substance are sealed with a sealing resin.

175 (New). The semiconductor light-emitting device according to Claim 157, wherein

the base substance is a lead frame having a cup-shaped mount section;

the semiconductor light-emitting element is disposed at the bottom of the cup-shaped mount section of the lead frame and electrically connected to another lead frame by wire bonding;

a coating member is filled in the cup-shaped mount section and the fluorescent substance is disposed on the coating member; and

at least a part of the two lead frames, the semiconductor light-emitting element, the coating member and the fluorescent substance are sealed with a sealing resin.



176 (New). The semiconductor light-emitting device according to Claim 158, wherein

the base substance is a lead frame having a cup-shaped mount section;

the semiconductor light-emitting element is disposed at the bottom of the cup-shaped mount section of the lead frame and electrically connected to another lead frame by wire bonding;

a coating member is filled in the cup-shaped mount section and the fluorescent substance is disposed on the coating member; and

at least a part of the two lead frames, the semiconductor light-emitting element, the coating member and the fluorescent substance are sealed with a sealing resin.

177 (New). The semiconductor light-emitting device according to Claim 159, wherein

the base substance is a lead frame having a cup-shaped mount section;

the semiconductor light-emitting element is disposed at the bottom of the cup-shaped mount section of the lead frame and electrically connected to another lead frame by wire bonding;

a coating member is filled in the cup-shaped mount section and the fluorescent substance is disposed on the coating member; and

at least a part of the two lead frames, the semiconductor light-emitting element, the coating member and the fluorescent substance are sealed with a sealing resin.

178 (New). The semiconductor light-emitting device according to Claim 160, wherein

the base substance is a lead frame having a cup-shaped mount section;

the semiconductor light-emitting element is disposed at the bottom of the cup-shaped mount section of the lead frame and electrically connected to another lead frame by wire bonding;

a coating member is filled in the cup-shaped mount section and the fluorescent substance is disposed on the coating member; and

at least a part of the two lead frames, the semiconductor light-emitting element, the coating member and the fluorescent substance are sealed with a sealing resin.

179 (New). The semiconductor light-emitting device according to Claim 161, wherein

the base substance is a lead frame having a cup-shaped mount section;

the semiconductor light-emitting element is disposed at the bottom of the cup-shaped mount section of the lead frame and electrically connected to another lead frame by wire bonding;

a coating member is filled in the cup-shaped mount section and the fluorescent substance is disposed on the coating member; and

at least a part of the two lead frames, the semiconductor light-emitting element, the coating member and the fluorescent substance are sealed with a sealing resin.

180 (New). The semiconductor light-emitting device according to Claim 157, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected the metallic wiring on the substrate;

a sealing resin for sealing the semiconductor light-emitting element is included; and

the sealing resin contains the fluorescent substance.

181 (New). The semiconductor light-emitting device according to Claim 158, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected the metallic wiring on the substrate;

a sealing resin for sealing the semiconductor light-emitting element is included; and

the sealing resin contains the fluorescent substance.

182 (New). The semiconductor light-emitting device according to Claim 159, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected the metallic wiring on the substrate;

a sealing resin for sealing the semiconductor light-emitting element is included; and

the sealing resin contains the fluorescent substance.

183 (New). The semiconductor light-emitting device according to Claim 160, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected the metallic wiring on the substrate;

a sealing resin for sealing the semiconductor light-emitting element is included; and

the sealing resin contains the fluorescent substance.

184 (New). The semiconductor light-emitting device according to Claim 161, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected the metallic wiring on the substrate;

a sealing resin for sealing the semiconductor light-emitting element is included; and

the sealing resin contains the fluorescent substance.

185 (New). The semiconductor light-emitting device according to Claim 157, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate and disposed in a recessed portion; and

the fluorescent substance is filled in the recessed portion.

186 (New). The semiconductor light-emitting device according to Claim 158, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate and disposed in a recessed portion; and

the fluorescent substance is filled in the recessed portion.

187 (New). The semiconductor light-emitting device according to Claim 159, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate and disposed in a recessed portion; and

the fluorescent substance is filled in the recessed portion.

188 (New). The semiconductor light-emitting device according to Claim 160, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate and disposed in a recessed portion; and

the fluorescent substance is filled in the recessed portion.

189 (New). The semiconductor light-emitting device according to Claim 161, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate and disposed in a recessed portion; and

the fluorescent substance is filled in the recessed portion.

190 (New). The semiconductor light-emitting device according to Claim 185, wherein

the recessed portion is formed by a frame disposed on the substrate.

191 (New). The semiconductor light-emitting device according to Claim 157, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate and disposed in a recessed portion;

a sealing resin is filled in the recessed portion; and

the fluorescent substance is disposed on the sealing resin.

- 192 (New). The semiconductor light-emitting device according to Claim 158, wherein
- the base substance is a substrate provided with metallic wiring;
  - the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate and disposed in a recessed portion;
  - a sealing resin is filled in the recessed portion; and
  - the fluorescent substance is disposed on the sealing resin.
- 193 (New). The semiconductor light-emitting device according to Claim 159, wherein
- the base substance is a substrate provided with metallic wiring;
  - the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate and disposed in a recessed portion;
  - a sealing resin is filled in the recessed portion; and
  - the fluorescent substance is disposed on the sealing resin.
- 194 (New). The semiconductor light-emitting device according to Claim 160, wherein
- the base substance is a substrate provided with metallic wiring;
  - the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate and disposed in a recessed portion;
  - a sealing resin is filled in the recessed portion; and
  - the fluorescent substance is disposed on the sealing resin.

195 (New). The semiconductor light-emitting device according to Claim 161, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate and disposed in a recessed portion;

a sealing resin is filled in the recessed portion; and

the fluorescent substance is disposed on the sealing resin.

196 (New). The semiconductor light-emitting device according to Claim 157, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

the fluorescent substance is contained in the sealing resin.

197 (New). The semiconductor light-emitting device according to Claim 158, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

the fluorescent substance is contained in the sealing resin.

198 (New). The semiconductor light-emitting device according to Claim 159, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

the fluorescent substance is contained in the sealing resin.

199 (New). The semiconductor light-emitting device according to Claim 160, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;



a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

the fluorescent substance is contained in the sealing resin.

200 (New). The semiconductor light-emitting device according to Claim 161, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

the fluorescent substance is contained in the sealing resin.

201 (New). The semiconductor light-emitting device according to Claim 157, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a shielding body for shielding light directly emitted from the semiconductor light-emitting element to the outside of the semiconductor light-emitting device is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the reflector that reflects light.

202 (New). The semiconductor light-emitting device according to Claim 158, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a shielding body for shielding light directly emitted from the semiconductor light-emitting element to the outside of the semiconductor light-emitting device is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the reflector that reflects light.

203 (New). The semiconductor light-emitting device according to Claim 159, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a shielding body for shielding light directly emitted from the semiconductor light-emitting element to the outside of the semiconductor light-emitting device is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the reflector that reflects light.

204 (New). The semiconductor light-emitting device according to Claim 160, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a shielding body for shielding light directly emitted from the semiconductor light-emitting element to the outside of the semiconductor light-emitting device is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the reflector that reflects light.

205 (New). The semiconductor light-emitting device according to Claim 161, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a shielding body for shielding light directly emitted from the semiconductor light-emitting element to the outside of the semiconductor light-emitting device is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the reflector that reflects light.

206 (New). The semiconductor light-emitting device according to Claim 157, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

at least a light-emitting section of the semiconductor light-emitting element is disposed in a recessed portion in the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the reflector that reflects light.

207 (New). The semiconductor light-emitting device according to Claim 158, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

at least a light-emitting section of the semiconductor light-emitting element is disposed in a recessed portion in the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the reflector that reflects light.

208 (New). The semiconductor light-emitting device according to Claim 159, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

at least a light-emitting section of the semiconductor light-emitting element is disposed in a recessed portion in the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the reflector that reflects light.

209 (New). The semiconductor light-emitting device according to Claim 160, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

at least a light-emitting section of the semiconductor light-emitting element is disposed in a recessed portion in the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the reflector that reflects light.

210 (New). The semiconductor light-emitting device according to Claim 161, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

at least a light-emitting section of the semiconductor light-emitting element is disposed in a recessed portion in the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the reflector that reflects light.

211 (New). The semiconductor light-emitting device according to Claim 157, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the sealing resin that reflects light.

212 (New). The semiconductor light-emitting device according to Claim 158, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the sealing resin that reflects light.

213 (New). The semiconductor light-emitting device according to Claim 159, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the sealing resin that reflects light.

214 (New). The semiconductor light-emitting device according to Claim 160, wherein



the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the sealing resin that reflects light.

215 (New). The semiconductor light-emitting device according to Claim 161, wherein

the base substance is a substrate provided with metallic wiring;

the semiconductor light-emitting element is electrically connected to the metallic wiring on the substrate;

a reflector for reflecting at least a part of outgoing light from the semiconductor light-emitting element is included;

a sealing resin for sealing the semiconductor light-emitting element and transmitting reflected light from the reflector is included; and

a layer of the fluorescent substance is formed on a surface of the sealing resin that reflects light.

216 (New). A semiconductor light-emitting device constituted by mounting a semiconductor light-emitting element on a base substance, wherein

the semiconductor light-emitting element has outgoing light having emission wavelengths of 390 to 420 nm;

a first fluorescent substance, a second fluorescent substance and a third fluorescent substance are included;

the first fluorescent substance has red outgoing light having emission wavelengths with its main emission peak in a wavelength range of 600 to 670 nm;

the second fluorescent substance has green outgoing light having emission wavelengths with its main emission peak in a wavelength range of 500 to 540 nm;

the third fluorescent substance has blue outgoing light having emission wavelengths with its main emission peak in a wavelength range of 410 to 480 nm; and

the sum of colors of light emitted from the first, second and third fluorescent substances is a white color, wherein

the first fluorescent substance is composed of any one or more selected from a fluorescent substance group consisting of:

$M_2 O_2 S$ : Eu (M is any one or more elements selected from La, Gd and Y);

$0.5MgF_2 \cdot 3.5MgO \cdot GeO_2$  : Mn;

$Y_2 O_3$  : Eu,

$Y(P, V) O_4$  : Eu; and

$YVO_4$  : Eu;

the second fluorescent substance is composed of any one or more selected from a fluorescent substance group consisting of:

$\text{RMg}_2\text{Al}_{16}\text{O}_{27}$  : Eu, Mn (R is any one or both elements selected from Sr and Ba);

$\text{RMgAl}_{10}\text{O}_{17}$  : Eu, Mn (R is any one or both elements selected from Sr and Ba);

$\text{ZnS}$ : Cu;

$\text{SrAl}_2\text{O}_4$  : Eu;

$\text{SrAl}_2\text{O}_4$  : Eu, Dy;

$\text{ZnO}$ : Zn;

$\text{Zn}_2\text{Ge}_2\text{O}_4$  : Mn;

$\text{Zn}_2\text{SiO}_4$  : Mn; and

$\text{Q}_3\text{MgSi}_2\text{O}_8$  : Eu, Mn (Q is any one or more elements selected from Sr, Ba and Ca);

and






the third fluorescent substance is composed of any one or more selected from a fluorescent substance group consisting of:

$\text{A}_{10}(\text{PO}_4)_6\text{Cl}_2$  : Eu (A is any one or more elements selected from Sr, Ca, Ba, Mg and Ce);

$\text{XMg}_2\text{Al}_{16}\text{O}_{27}$  : E (X is any one or both elements selected from Sr and Ba);

$\text{XMgAl}_{10}\text{O}_{17}$  : Eu (X is any one or both elements selected from Sr and Ba);

$\text{ZnS}$ : Ag;



217 (New). The semiconductor light-emitting device according to Claim 216, wherein, assuming the total amount as 100 weight %,

the first fluorescent substance is between 50 weight % and 70 weight % inclusive;

the second fluorescent substance is between 7 weight % and 20 weight % inclusive;

and

the third fluorescent substance is between 20 weight % and 30 weight % inclusive.

218 (New). The semiconductor light-emitting device according to Claim 217, wherein

the sealing resin contains the first, second and third fluorescent substances; and

the proportion of the total weight of the first, second and third fluorescent substances to the weight of the sealing resin is between 0.5 and 1 inclusive.

219 (New). A light-emitting display device comprising;

a light source using the semiconductor light-emitting device according to Claim 216;

a light guiding plate for guiding light from the light source; and

red, green and blue color filters for transmitting light from the light guiding plate and dividing the light; the light-emitting display device, wherein

outgoing light from the semiconductor light-emitting device has a wavelength distribution that matches spectral characteristics of the color filters.

220 (New). The light-emitting display device according to Claim 219, wherein at least one of the following is adjusted so that the wavelength distribution of the outgoing light from the semiconductor light-emitting device matches spectral characteristics of the color filters:

the emission wavelength of the semiconductor light-emitting element;

the emission wavelength of the first fluorescent substance;

the emission wavelength of the second fluorescent substance;

the emission wavelength of the third fluorescent substance;

the mixture proportions of the first, second and third fluorescent substances; and

the proportion of the total weight of the first, second and third fluorescent substances to the weight of the sealing resin.

221 (New). The light-emitting display device according to Claim 219, wherein

the light-emitting display device is a liquid crystal display device.

222 (New). The light-emitting display device according to Claim 220, wherein

the light-emitting display device is a liquid crystal display device.